



**Manufacturer of Specialty Chemicals**

## **“MORTARLIFE”**

Additive for extending the working time of Mortar. MortarLife is an additive used with Portland cement/lime mortars and proprietary mortar and masonry cements to extend the working time of mortar.

**Addition Rate:** (at 21°C): Add 50 ml MortarLife per 30 kg of combined cement and lime for conventional mortar or 25 ml per 30 kg of Masonry Cement/Mortar Cement. Temperature, humidity and other factors will affect the addition rate of MortarLife, refer to product data sheet. Trial mixes are recommended.

**Mixing:** Add 1/3 of sand, 100% of the cementitious materials, and sufficient water to produce a slurry. Add MortarLife in the recommended or field-tested dosage. Add remaining sand and then water to the desired consistency. Mix for 3-5 minutes. Minimum temperature for applications is 1°C. Protect containers from direct sunlight. Keep from Freezing.

### **Laboratory Analysis:**

|             |                  |
|-------------|------------------|
| Appearance: | Clear/Pale green |
| Odour:      | None             |
| Solubility: | Water soluble    |
| Toxicity:   | Non-toxic        |
| pH:         | 8 -12            |

Packaging: 4 litre jug  
20 litre pail  
205 litre drum



This product is not controlled under WHMIS.  
For further information consult the safety data sheet and label

Visit us at our website [www.chemfax.com](http://www.chemfax.com)